

Specification of Desiccant bags

PART No. 105-MD-



Product Information:

- Bentonite Clay Dessicants, which is environmentally friendly and easily disposed of after use
- For use with moisture barrier bags
- Non woven with dissipative coating
- Unit Weight 25, 50 & 100 grams
- Using Temperature up to 50 deg C
- Moisture: Efficient from 15% to 50% RH
- Moisture Absorption: 5.9 grams/unit of H₂O at 20% RH; 6.8 gram/unit @ 40% RH
- Reactivation: 120 deg C (245 F) for 16 hours
- Complies to EN 61340-5-1 and MIL-D-3464E

ABOUT KAISERTECH

Founded in 1998, Kaisertech Ltd is situated in Eastleigh, Hampshire.

Through hard work and dedication Kaisertech has grown to be a well-recognized supplier of electronic production equipment and tools.

Specialists in: Soldering, Static Control, Vision, Industrial Furniture, Electric crew Drivers & Special Projects.