

# **Technical Data Sheet**

KingsFlux Acid Cored Solder
Wire

Issue No. 1.02 October 2020

## **Description**

SolderKing KingsFlux Acid Cored Solder Wire is a highly active solder wire suitable for effective soldering of heavily oxidised finishes. Rapid soldering can be achieved on most common metals excluding Aluminium.

KingsFlux Acid Cored Solder Wire has been developed for excellent thermal stability and can be used under prolonged heat conditions including flame or torch soldering.

This product is not suitable for electronic applications due to the corrosive nature of the flux and post soldered residues should be removed with warm water

# **Solder Alloy**

KingsFlux Acid Cored Wire is manufactured using high purity virgin metals. Solderking uses due diligence in the manufacture of solder wire and uses metals which are 'conflict free' as per the Dodd-Frank Conflict Minerals Law 1502.

Solderking Part	Alloy	Melting point °C
96/S	Sn96.5Ag3.5	221
96/4	Sn96Ag4	221
40/60	Sn40Pb60	183-234
60/40	Sn60Pb40	183-188
99c	Sn99.3Cu0.7	227

## Wire Gauge

KingsFlux Acid Cored Wire is available in wire diameters from 3.25mm to 0.315mm. Custom diameters are available.

## **Safety Information**

Always read safety data sheet before use. For any further Information please contact:

info@solderking.com.



#### **Benefits**

Highest activity available

Residues easily removed

RoHS compliant and leaded alloys available

Low odour, non-offensive fume

Easy to use

**Excellent thermal stability** 

# **Availability**

Packaging and modifications are available on request.

Solder Wire	Packaging
KingsFlux Acid Cored	500g
Solder Wire	250g
	2.5Kg
	3Kg

The information supplied in this technical data sheet is designed only as guidance for use and handling of the product. This information is correct to the best of our knowledge and belief at the date of publication however no guarantee is made to its accuracy. This information related only to the specific material designated and may not be valid for such material used in combination with any other materials or in any other process.

