



Anti-Corrosion

RAPID DRY GALVA

VERY FAST DRYING PROTECTIVE COATING

Rapid Dry Galva is an exceptionally fast drying anti-corrosion paint that matches the finish of recently hot-dip galvanised steel. With an optimal blend of adhesive resin binders, opacity enhancers, metallic pigments and zinc phosphate; Ambersil 'Rapid Dry Galva' delivers long-lasting corrosion prevention to cut, drilled, and damaged galvanised steel.

- Rapid drying time: Touch dry in 2 mins/ Hard dry in 20 mins at 20°C
- Excellent colour-match for recently/ shiny hot-dip galvanised steel
- Effective protection against corrosion (tested to ASTM B117)
- Excellent substrate adhesion & flexibility (tested to ISO 2409:0)

PRODUCT CODES / FILL SIZES



33280 / 400ml

APPLICATIONS

- Use where production and repair timescale do not allow the use of slower drying products.
- Rapid Dry Galva is the ideal product choice for sealing drill holes and cut surfaces in recently hot-dip galvanised steel.

DIRECTIONS

- Use in well ventilated area.
- Remove any rust and scale with a wire brush. Ensure that the surface to be coated is clean, dry and free from grease.
- Rapid Dry Galva contains solids which settle during storage: shake the can vigorously until the agitator ball is free and continue shaking for a further minute.
- Shake the can periodically during application.
- Apply in light, even coats - best results are obtained with 2 – 3 light coats rather than one heavy coat.
- Additional coats can be applied after 15 - 20 minutes.
- When spraying is finished, clean the aerosol valve by turning the can upside down and spray until only propellant escapes.
- Do not use on the inside of water storage tanks.
- Remove prior to welding.

TECHNICAL DATA (WITHOUT PROPELLANT)

Appearance	Silver/zinc colour matched to recently galvanised metal
Odour	Solvent
Drying Time	120 seconds touch dry. Cured: 24 hours
Temperature Resistance	Cured film: -30°C to 150°C
Recommended Film Thickness	20-30 µm
Adhesion to steel (ASTM D 3359)	GT= 0/1
PersoZ hardness (after 72 h)	80 s

MATERIALS COMPATIBILITY

OK	Suitable for use on most metals
CAUTION	-
NOT OK	Plastics and rubers

STORAGE & SHELF LIFE

The product may be stored at normal ambient temperatures and has a shelf life of not less than 6 years with correct storage. Aerosols should always be stored below 50°C, away from direct heat and naked flame.

HEALTH AND SAFETY

A separate Safety Data Sheet (SDS) according to EC Regulation 73/404/EEC and 648/2004/EC is available from Ambersil.com or via info.uk@crcind.com

MISREPRESENTATION ACT 1967

TRADE DESCRIPTIONS ACT 1968

The information given in this publication is based on our experience and reports from customers. There are many factors outside our control and knowledge which affect the use and performance of our products and for which reason no warranty is given, express or implied. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.

Version 4.0
Created: July 2019
Updated: June 2021

CRC Industries UK Ltd.
Wylds Road, Bridgwater
Somerset, TA6 4DD
United Kingdom

t +44 (0)1278 727200
f +44 (0)1278 425644
e sales.uk@crcind.com
www.ambersil.com

Company Registered No. 04910479

VAT No. GB 821 5195 42

