PRODUCT

ESD Flux Bottles

New development process of moulding polyethylene bottles utilising a concentrate that does not contain any Exthoxylated Tertiary Amine, which is widely used as an antistatic agent. These ESD safe bottles have an average surface resistivity of 109 to 1010 ohms/square and do not have any less desirable features associated with surfactant laden material.

These bottles will dissipate a static charge of ±5000V in less than two seconds at 40% relative humidity. By their chemical nature, they will not have any chemical reactivity with solvents as TCE or alcohol.



FEATURES

- Static Free
- Non-Greasy
- No Tertiary Amines
- Humidity Independent
- Average Surface Resistivity of 109 to 1010 ohms/Square
- Helps to Meet ANSI/ESD S20.20